

**HOWARD COUNTY DEPARTMENT OF PUBLIC WORKS
CORROSION CONTROL TEST STATION
FIELD DATA SURVEY FORM**

Location: Cedar Ave. and Donald Ave. Date Surveyed: 06/13/2007
 T/S #: 08 Surveyed by: AS/MJ
 T/S Type: ST w/Anode Contract #: 24-3811
 Pipe Size: 8"
 Was the T/S located? YES / NO YES

TEST STATION CONDITION

Test Box:	<u>Good</u>
Terminal Board:	<u>Good</u>
Wires:	<u>Good</u>
Other:	

SURVEY DATA

Test Wire Size/Description	Color	P/Cu-CuSO ₄ (V)		P/Zn (V)		Anode (mA)
		"On"	"Off"	"On"	"Off"	
1. #10 AWG	Blue	-0.932	-0.775	-1.139	-0.892	83
2.						
3. #10 AWG	Blue	-0.947	-0.783	-1.134	-0.892	
4. #6 AWG	Black	-0.957	-1.502	-1.139	-1.620	
5.						
6. #8 AWG	Black	0.145	0.060			
7.						
8.						

P/Cu-CuSO₄ = Pipe to Copper-Copper Sulfate Reference Electrode
 P/Zn = Pipe to Zinc Reference Electrode
 "On" = Reading with Anode(s) connected
 "Off" = Reading with Anode(s) disconnected
 Anode = Current output Anode(s)

TESTING THE EFFECTIVENESS OF INSULATING JOINTS

Groundbed:			
Connected to (B/W):			
	Current (A)	Voltage (V)	Resistance (ohms)
ON:			
OFF:			
DELTA:			

TESTING IR DROP

IR Drop Calibrations	I (A)	E (mV)	$K = \frac{\Delta I \text{ (mA)}}{\Delta E \text{ (mV)}}$ Direction:	Between Terminals	Resistance (ohms)
INITIAL:					
FINAL:					
DELTA:					

REPAIRS MADE

Test Box:	
Terminal Board:	
Wires:	
Other:	
Comments/Recommendations:	



Figure 198 - Location of Test Station 3811-8



Figure 199 - Test Station 3811-8 close-up